

SIKA
MARINE



THE
PROFESSIONAL'S
CHOICE

Sikaflex®-290 DC PRO THE PROFESSIONAL DECK CAULKING SEALANT

- Sandable, that's easy and fast
- Excellent weathering resistance
- Robust and durable
- Professional use only
- IMO certified

Sikaflex®

**290 DC
PRO**

Deck Caulking System

Sistema para el
calafateado de cubiertas

Sistema de calafetagem
de convés

Σύστημα Σφράγισης
Αρμών Καταστρωμάτων

▶ UV- and weatherproof deck caulking
sealant. Sandable.

▶ Sellador para el calafateado de
cubiertas resistente a la radiación
ultravioleta y a la intemperie.
Puede lijarse.

▶ Selante para calafetagem de convés
resistente aos UV's e ao tempo e que
pode ser lixado

▶ Σφραγιστικό για αρμούς
καταστρωμάτων με αντίσταση σε
ηλιακή ακτινοβολία και καιρικές
επιδράσεις. Μπορεί να τριφτεί

300 ml

BUILDING TRUST



Sikaflex[®]-290 DC PRO

Sikaflex[®]-290 DC PRO is a 1-component polyurethane based joint sealing compound, specifically formulated for caulking joints in traditional timber marine decking. It exhibits excellent weathering resistance and is therefore well suited for highly exposed open joints within the marine environment.

For specific applications consult the product data sheet or contact your Sika Technical Service.

PRODUCT BENEFITS

- Flexible
- Well suited for highly exposed open joints
- Long toolability
- Resistant to seawater and fresh water

AREAS OF APPLICATION

- Caulking of joints in traditional timber decking
- Boats, yachts, commercial ships



Typical Product Data

Chemical base	1-C Polyurethane
Cure mechanism	Moisture curing
Density (uncured) (CQP006-4)	1.3 kg/l
Application temperature	5 - 35°C
Skin time (CQP019-1)	90 minutes approx ^A
Shore A hardness (CQP023-1/ ISO 868)	40
Tensile strength (CQP020-3)	3 MPa
Elongation at break (CQP020-3)	600% approx
Shelf life (storage below 25°C) (CQP016-1)	9 months for pail

CQP = Corporate Quality Procedure ^A23°C/50% r.h

Our most current General Sales Conditions shall apply.

Please consult the most current local Product Data Sheet prior to any use..



SIKA LIMITED

Head Office
Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
United Kingdom

Contact

Phone +44 1 707 394444
E-Mail sealingandbondingenquiries@uk.sika.com
www.sika.co.uk/sealantsandadhesives
@SikaLimited

SIKA IRELAND LIMITED

Sika House
Ballymun Industrial Estate
Dublin 11
D11 DA2V
Ireland

Contact

Phone +353 1 862 0709
Fax +353 1 862 0707
E-Mail info@ie.sika.com
www.sika.ie
@SikaIreland

BUILDING TRUST

